

HEGGEL® Pox 416

All-Purpose Low-Viscosity Epoxy Resin

You Build, We Protect!

Description:

HEGGEL Pox 416 is a high-quality low-emission, and all-purpose applicable, two-component epoxy resin based on the exceptionally established **HEGGEL Pox 410**.

Use **HEGGEL Pox 416** as base coat, for scratch coats, or as levelling mortar for reconstruction or new constructions. Due to its low-viscosity and good wettability properties the resin penetrates very well into the substrate and develops a high-strength base for subsequent coatings.

Characteristics:

- High solid content
- Low VOC emission
- All-purpose usage
- Safe and reliable
- High-quality base coat
- Resistant to hydrolysis and saponification
- Free of deleterious substances against varnish

Applications:

- Low-emission base coat
- As base coat, for scratch coats, and prime filling coats.
- Levelling coatings and epoxy resin mortar.

Application Data:

Mixing Ratio	Parts by Weight	A : B = 100 : 50		
	Parts by Volume	A : B = 100 : 53		
Processing Temperature		Minimum 10°C (room- and floor-temperature)		
Further Coatings		After curing, but not longer than 48 hours at 20°C		
Consumption	Base coat	Approx. 0.250 - 0.350 kg/m ²		
	Scratch coat	Approx. 0.450 - 0.600 kg/m ²		
	Mortar	Approx. 0.150 - 0.300 kg/m ²		
@Temperature		10°C	20°C	30°C
Curing Time	Accessibility	14 - 18 hrs	7 - 10 hrs	5 - 7 hrs
	Mechanical Load	-	2 - 3 days	-
	Chemical Load	-	7 days	-
Processing Time		50 min	30 min	15 min

Technical Data:

Title	Standard	Value	Unit
Viscosity (Components A + B)	DIN EN ISO 3219 (23°C)	550	mPas
Solid Content	HEGGEL-Method	> 99.9	%
Density (Components A + B)	DIN EN ISO 2811-2 (20°C)	1.10	kg/L
Weight Loss	After 28 days	0.3	Weight %
Water Absorption	DIN 53495	< 0.2	Weight %
Bending Tensile Strength	DIN EN 196/1	35	N/mm ²
Compressive Strength	DIN EN 196/1	80	N/mm ²
Shore-Hardness D	DIN 53505 (after 7 days)	80	-
Adhesive Tensile Strength	DIN EN ISO 1542	> 1.5	N/mm ²

Note: Values achieved in sampling are average values. Variation in product specification is possible.

Packaging:

Hobbock-Combi 30 kg

Storage:

12 months in sealed original containers under dry and cool conditions between 10 - 20 °C. Bring to a suitable working temperature before application. Tightly re-seal opened containers and use the content as soon as possible. Protect from heat and freeze!

1. Surface Preparation

The substrate to be coated has to be levelled, dry, free of dust, has to have adequate tensile and compressive strength, and be free from weakly-bonded components or surfaces. Materials impairing adhesion, such as grease, oil, and paint residues must be removed using suitable methods. Suitable surfaces are concrete C20/25, cement screed CT-C35-F5, as well as other adequately sound surfaces. The substrate must have adequately high strength for the proposed occupational use. The coating of mastic asphalt with epoxy resin is not recommended. The surface to be coated should be prepared mechanically, preferably by shot-blasting. The surface strength must then be a minimum of 1.5 N/mm². For concrete, moisture content must not exceed 4.5 CM%, remaining residual humidity. The possibility of moisture ingress from the rear must be permanently excluded. Reconstructing floors may need special procedures. Please obtain technical advice where necessary.

2. Mixing

Combi-trading units will be supplied in the correctly measured mixing ratio. Component A has sufficient volume for the entire trading unit. Decant the hardener compound B into the resin component A completely. Blend with a slow speed mixer (200 - 400 rpm) for at least 2 - 3 minutes, for a material that is homogeneous and free of streaks. To avoid mixing errors it is recommended to empty the mixed resin into a clean container and mix briefly once again ("to repot").

Producing scratch coats and mortar:

Scratch coats:

1.0 kg	HEGGEL Pox 416
0.5 - 0.8 kg	HEGGEL quartz sand-mix 2/1

Epoxy resin mortar:

1.0 kg	HEGGEL Pox 416
8.0 - 12.0 kg	HEGGEL quartz sand-mix 1

Premix the resin before adding any additives. The amount of the sand blend to be added depends on the desired texture and consistency.

3. Processing / Handling

Base Coat: If the material is used as a base coat process immediately after mixing with a coating knife, spatula, or nylon roller. Apply an evenly closed sealing coat on the surface. On highly absorbent surfaces a second coat or a saturated scratch coat is recommended to achieve a fully sealed surface with closed pores. Scatter the surface with quartz sand (grain size 0.3 / 0.8 mm) for an optimum adhesion while the applied material is still fresh. This is mandatory if the subsequent coatings will be applied later than 24 hours after base coat application.

Scratch Coat: For smoothing and completely sealing the substrate apply a scratch coat before the application of any subsequent coatings. This can be done with a trowel, metal, or rubber coating knife. The consistency has to be adjusted according to the absorbency of the substrate and set so the material may run true.

Priming Filler: The base coat may be applied as prime filling coat simultaneously. It just has to be assured that a sufficient sealing surface is applied in one coat for the subsequent coatings. Usually prime filling coats may be filled with 0.5 kg of **HEGGEL quartz sand-mix 2/1** for each 1 kg of epoxy resin. Apply with a smooth rubber spatula, with a consumption of 0.7 - 1.0 kg/m², depending on the depth of roughness of the substrate.

Epoxy Resin Mortar: For repair work the mortar can be made of **HEGGEL Pox 416**. It is recommended to use special resins like **HEGGEL Pox 480** for industrial mortar coatings. Process immediately after mixing. Pull off the mortar with a lath, compact and smooth with a smoothing trowel. Clean tools with small amounts of **Cleaner V20** if necessary.

Floor -and air- temperature must not fall below 10 °C and humidity must not exceed 75%. The difference in floor -and room-temperature must be less than 3 °C, so the curing will not be disturbed. If a dew point situation occurs adhesion may malfunction, curing may be disturbed, and spotting may occur. Curing time applies to 20 °C. Lower temperature may increase, higher temperature may decrease the curing and processing time. If working conditions are not complied with, deviations in the described technical properties may occur in the end product.

Special Remarks: We advise against the "gumming" of screed joints / flat joints with pure or with thixotropic agent filled epoxy resin. In the course of time, these areas will begin to show on the surface. For the application, use always the HEGGEL-Primer resin in combination with quartz sand e.g. **HEGGEL quartz sand-mix 1** or **HEGGEL quartz sand-mix 2/1**. For this, we recommend to add at least 1 - 3 parts by weight of filler.

4. Cleaning

To remove fresh contamination and to clean tools, use **Cleaner V20** or **V30** immediately. Hardened material can only be removed mechanically.

5. Safety Measures

The product is subject to the hazardous material, operational safety, and transport regulations for hazardous goods. Refer to the DIN-Safety Data Sheet and the information on the labelled containers!

GISCODE (05/2018 modification): RE 30

6. VOC-Contents

The product complies with the high requirements to low VOC-contents, as required for sustainable construction. Therefore, these values exceed by far the European Union directive 2004/42/EG (decopaint-directive)

	Reference to	Max. Value	Actual Content
Directive 2004/42/EG Decopaint-directive	Component A	≤ 500 g/L	0.25 g/L
	Component B	≤ 500 g/L	0 g/L
DGNB German Sustainable / Building Council	Components A + B	< 3 %	0.17 %
Climate:active Climate protection initiative of the Austrian Federal Ministry of Agriculture, Forestry, Environment and Water	Components A + B	< 3 %	0.17 %
LEED Leadership in Energy and Environmental Design	Components A + B	< 100 g/L	1.9 g/L
Minergie Eco® Quality standard of the "Minergie society", Switzerland	Components A + B	< 1 (< 2) %	0.17 %

Note: According to the decopaint-directive single components are used for the calculation. For the quality rating system for sustainable construction the mixture of both components in the correct mixing ratio is the determining factor.

HEGGEL Pox 416; Revision No: 1.10 / Last Revision Date: 18.09.2023

All information contained herein is based on the current state of our knowledge and practical experience at the time of release. Therefore, please make sure that this is the latest edition of the Technical Data Sheet. All data are only intended as a guideline for informational purposes and do not constitute a legally-binding warranty of the suitability for a certain purpose of use, due to its dependence on site conditions and possible processing, use and applications. All information contained in this technical datasheet is subject to change without notice.

HEGGEL GmbH

Huttropstr. 60
45138 Essen
Germany

Tel: +49 201 17003 270

Fax: +49 201 17003 277

E-Mail: info@heggel.de

Web: www.heggel.de